TECHNICAL SPECIFICATIONS

Quality : AL collection

Yarn Fiber : 100% Luxatron

Width : 3.66M

Pile Weight : \pm 38 oz./yd² (1,280 g/m²)

Pile Height : ± 8.5 mm

Total Height : ± 10.0 mm

Gauge and Structure : 1 / 10 " Cut pile Machine Tufted

Stitch Rate : 29 stitches per 3 inches

Primary Backing : 100% Woven Polypropylene

Secondary Backing : Action Back

Fire Class : SGS BS 5287 : 1988/ BS 4790 : 1987

: CPSC FF-1-70 / ASTM D 2859-96

Colourfastness : AATCC Test Method 16 Option E (Grade 4)

Electrical Behaviour : AATCC 134-1996

Soil & Stain Protection : Yes

CRI : GLP # 4088

Original : Made in Mexico (USA Group)



Test Report

No. 2705253/TX

Date: Jul 29 2006

Page 1 of 2

SAM YUEN CARPET DEVELOPMENT LIMITED RM 701, RIGHTFUL CENTRE 11-12 TAK HUNG STREET KOWLOON, HK.

The following sample was submitted and identified by the client as:

One sample of CE Collection carpet in CE-05.

Yarn Composition

100% luxatron

Tufted Construction

Cut-pile

Width

12'-0" (3.66M)

Primary Backing

Woven polypropylene

Secondary Backing

Action Back

Tufting Pile Weight

+ 1,220 g/m² (36 oz. / Yd²)

Tufting Pile Height

+ 8.5mm

Gauge

1/8"

Stitch Rate

26.5 stitches / 3"

Tuft Bind

48 oz. Min

Laminant

2.5 lbs per inch

Sample Receiving Date

Jul 25, 2006

Test Performing Date

Jul 26, 2006

Test Performed

Selected test(s) as requested by applicant.

Test Results

Please refer to the next page(s).

Conclusions

Ignition test

Pass

Signed for and on behalf of SGS Hong Kong Ltd.

Wong Wing Kwan, Connie Account Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf or available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated: (a) the results shown in this document refer only to the sample(s) tested and (b) such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law. H13797538



Test Report

No. 2705253/TX

Date: Jul 29 2006

Page 2 of 2

Test Result:

Ignition Test On Textile Floor Coverings (BS 5287:1988 / BS 4790:1987, Hot metal nut method) The test results relate only to behaviour of the test specimens after application of a small source of ignition; they shall not be used as a means of assessing how the product will contribute to an established fire

Specimen	(1)	(2)	(3)	
(1) Use-surface (Radius of the affected area) (mm)	17	17	17	
(2) Under-surface (Radius of the affected area) (mm)	13	13	13	
Greatest radius of the affected area (mm):	17			
Flame extinction time (sec)	0	0	0	
Afterglow or smouldering (sec)	0	0	0	
Ignition to reach the clamping ring (sec)	0	0	0	
Burn Code	DNI	DNI	DNI	

Remarks

(1) DNI = Did not ignite

(2) Method of mounting test specimens: Method 1 - Loose - laid.

(3) The submitted sample complies with the requirement as stated in BS 5287: 1988 – Assessment and Labelling of textile floor coverings – "A specimen shall be considered as satisfactory if the radius of the affected area is not greater than 75mm."

(4) Labelling recommendation -:

Radius of affected area (mm)	Information given on label
up to 35	When tested according to the appropriate method of BS 4790 this floor covering has a low radius (up to 35 mm) of effects of ignition.

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf or available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated: (a) the results shown in this document refer only to the sample(s) tested and (b) such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.

Test Number: 254248

Independent / Textile

P.O. Box 1948

Service, Inc.

1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton.net

TEST REPORT

Customer:

Subject:

"Consumer Product Safety Commission (CPSC) FF 1-70"

"16 CFR 1630"

"ASTM D 2859-96"

Scope: This test method covers the determination of the flammability of finished textile floor covering materials when exposed to an ignition source under controlled laboratory conditions. It is applicable to all types of textile floor coverings regardless of the method of fabrication or whether they are made from natural or man-made fibers.

Sample Identification: Style: AL

FLAMMABILITY TEST

STYLE	COLOR	ROLL	TESTED	PASSED
Style: AL	7988	 -	8	8

APPROVED
MEETS OR EXCEEDS
FEDERAL FLAMMABILITY
STANDARD CPSC FF 1-70

L. Kent Suddeth

Test No: 254689

Independent / Textile

P.O. Box 1948

Service, Inc.

1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton.net

TEST REPORT

Customer:

August 18, 2005

Subject: Sample(s) of carpet submitted for testing by the customer and identified below:

Sample Identification: Cobe

Test Method Conducted

AATCC Test Method 16 Option E

Colorfastness to Light (Water-Cooled Xenon Arc)

Purpose and Scope

This test method provides the general principles and procedures which are currently in use for determining the colorfastness, to light of textile materials.

Procedure

Samples of the textile material to be tested and the agreed upon comparison standard(s) are exposed simultaneously to a light source under specified conditions. The colorfastness to light of the specimen is evaluated by comparison of the color change of the exposed portion to the masked or control portion of the test specimen using the AATCC Gray Scale for Color Change or by instrumental color measurement.

Style
Number of Cycles
Colors

Luxor 032
2 (40 AFU's)
CE-09
CE-18
CE-01
CE-02
CE-21
CE-06
CE-03
CE-05
CE-22
CE-32
CE-33
CE-34
CE-35

L. Kent Suddeth

Test No: 254689

Independent / Textile

P.O. Box 1948

Service, Inc.

1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton.net

TEST REPORT

Customer:

August 18, 2005

Subject: Sample(s) of carpet submitted for testing by the customer and identified below.

Sample Identification: Cobe

Test Method Conducted

AATCC Test Method 16 Option E

Colorfastness to Light (Water-Cooled Xenon Arc)

Purpose and Scope

This test method provides the general principles and procedures which are currently in use for determining the colorfastness, to light of textile materials.

Procedure

Samples of the textile material to be tested and the agreed upon comparison standard(s) are exposed simultaneously to a light source under specified conditions. The colorfastness to light of the specimen is evaluated by comparison of the color change of the exposed portion to the masked or control portion of the test specimen using the AATCC Gray Scale for Color Change or by instrumental color measurement.

- Style	Color	Temp.	Number of Cycles	Rating	
Luxor 032 (S)	8056	112°C	2 (40 AFU's)	4.5	
Luxor 032 (P)	8056	112°C	2 (40 AFU's)	4.5	
Luxor 032 (S)	8056	98°C	2 (40 AFU's)	5.0	
Luxor 032 (P)	8056	98°C	2 (40 AFU's)	5.0	
Luxor 032 (S)	0714	112°C	2 (40 AFU's)	4.5	
Luxor 032 (P)	0714	112°C	2 (40 AFU's)	4.5	
Luxor 032 (S)	0714	98°C	2 (40 AFU's)	4.5	
Luxor 032 (P)	0714	98°C	2 (40 AFU's)	4.0	

	Key to Ratings
5	Negligible or no change
4	Slight change
3	Noticeable change
2	Considerable change
1	Severe change

L. Kent Suddeth

Test No: 254032

Independent / Textile

P.O. Box 1948

Testins Service, Inc.

1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton.net

TEST REPORT

Customer:

June 24, 2005

Subject: Sample(s) of carpet submitted for testing by the customer and identified below:

Sample Identification: Cobe

Test Method Conducted

AATCC 134-1996

Electrostatic Propensity of Carpets

Purpose and Scope

This test method is designed to assess the static generating propensity of carpets developed when a person walks across them by controlled laboratory simulation of conditions which may be met in practice, and more particularly, with respect to those conditions which are known from experience to be strongly contributory to excessive accumulation of static charges.

Test Conditions:

Chamber Temperature: 70° F. Chamber Relative Humidity: 20%

Test Results:	Sole	Underlay	Maximum Voltage 1 (kV)	Maximum Voltage 2 (kV)	Averages (kV)
Test I Step Test	Neolite	H/J	Neg. 0.4	Neg. 0.3	Neg. 0.4
Test II Scuff Test	Neolite	H/J	Neg. 3.0	Neg. 3.2	Neg. 3.1
Test III Step Test	Leather	H/J	Neg. 2.0		
Test IV Scuff Test	Leather	H/J	Neg. 3.1		

Soles:

- a) Neolite XS 664
- b) Suede Leather

Underlayment:

a) Plate: Earth grounded metal plate

b) H/J: Standard 40 oz./yd2 rubberized Hair/Jute cushion

L. Kent Suddeth



Green Label PlusTM Indoor Air Quality Testing Program The Carpet and Rug Institute, Inc. PO Box 2048 Dalton Georgia 30722 USA Phone: +1(706) 428-2101 Fax: +1(706) 428-3101

Email: glpadmin@carpet-rug.org

www.carpet-rug.org

Green Label PlusTM Compliance Notice

January 27, 2017

Attention:

Monclova, Mitras Centro, 66550 Carmen, Nuevo León MEXICO

Test Type: Interim Annual for Carpet

GLP #: 4088

Test Report ID: 18300-516

Category: 1Y

Sample Collection Date: <u>December 21, 2016</u> Certification Expiration Date: December 31, 2017

The product identified above has been tested and determined to be IN COMPLIANCE with CRI's Green Label Plus Indoor Air Quality Testing Program. The test report is attached for your information.

For purposes of the Program's compliance, these test data are interpreted on a pass/fail basis, and are confidential in nature. This data is provided to your company for its internal use only. In accordance with the Participation Agreement, the specific information and details contained in accompanying test data are not to be used in your company's advertising or promotional materials. Any other use or distribution of this test data is prohibited without the written consent of CRI. Please contact CRI at glpadmin@carpet-rug.org if you have any questions about this notification. Thank you for your cooperation and participation in the Green Label Plus program.

Joe W. Yarorough

President

The Carpet and Rug Institute, Inc.

Green Label Plus Compliance Notice
Version.Revision: 1.02 Revised: May 26, 2016
Supersedes: Green Label Plus Compliance Notice (Version 1.01)

'Morlwoogh

Approved By: Joe W. Yarbrough Date: May 26, 2016

Page 1 of 1